



STOPGAP P131

General Purpose Neoprene Primer

PRODUCT DATA

INTRODUCTION

STOPGAP P131 is a neoprene primer designed to promote the adhesion of STOPGAP smoothing underlayments to smooth non-absorbent surfaces. It can also be used as a general purpose primer for absorbent surfaces to promote adhesion and to prevent unacceptably rapid drying of adhesives and smoothing underlayments. It is suitable for use over normal underfloor heating installations. STOPGAP P131 is coloured green to provide the user with visual control of coverage uniformity. STOPGAP P131 should be used on non-absorbent surfaces of STOPGAP Waterproof Surface Membranes, terrazzo, power floated concrete, quarry and ceramic tiles, sound asphalt, steel, well bonded epoxy and polyurethane coatings and minimal existing adhesive residue. It should also be used on absorbent surfaces such as concrete, sand/cement screeds, plywood, hardboard and chipboard.

PREPARATION

Floor surfaces must be suitably prepared: sound, smooth, dry (<75%RH) and free from contaminants that may prevent adhesion. Concrete and sand/cement screeds must be fully cured and any laitance or surface treatments must be removed prior to the application of the appropriate STOPGAP underlayment. The temperature of the surface must be above 10°C when the primer is applied to the subfloor and underfloor heating must be off for at least 48 hours before, during and after application. Ensure the subfloor is dry and incorporates an effective damp proof membrane.

MIXING AND APPLICATION

SHAKE WELL BEFORE USE

For absorbent surfaces add 1 part of STOPGAP P131 to 4 parts of clean cold water and stir until thoroughly dispersed. For non-absorbent surfaces, apply the primer neat. Apply STOPGAP P131 evenly to the whole surface to be treated and allow it to dry completely.

DRYING TIME

This will vary depending on the temperature, humidity and absorbency of the subfloor. On absorbent subfloors, at 20°C, allow 20 to 30 minutes before proceeding with the application of STOPGAP smoothing underlayments or STYCCOBOND adhesives. On non-absorbent subfloors, at 20°C, this is typically extended to 60 minutes. These times will be extended at lower temperatures.

PRECAUTIONS

Avoid excessive trafficking of the subfloor once the primer has dried.

TOOLS

Paint roller or medium stiff broom. Wash tools with warm water immediately after use.

STORAGE

Store between 5°C and 30°C. Protect from frost.

SHELF LIFE

12 months in unopened containers and stored under good conditions.

TECHNICAL INFORMATION

Colour	Green
Coverage Rates (Approx.)	Applied dilute to absorbent : 100m ² Applied neat to non-absorbent : 50m ² Rates will vary based on the condition of the subfloor
Drying Time (Approx.)	20 - 30 minutes at 20°C on absorbent subfloors 60 minutes at 20°C on non-absorbent subfloors

HOW MUCH MATERIAL?

PACK SIZE	COVERAGE PER UNIT
5 litres neat *	50m ²
5 litres diluted (4:1)**	100m ²

Note:

* Applied neat for non-absorbent surfaces.

** Applied diluted for absorbent surfaces.

The coverage rates will depend on the condition and absorbency of the subfloor.



FEATURES

- General purpose for both absorbent and non-absorbent surfaces
- Suitable for use with marine applications
- Prevents rapid drying of adhesives and smoothing underlayments
- Pigmented to provide coverage control

PACKAGES

5 litre bottle

HEALTH AND SAFETY ADVICE

This product is not classified under the Chemicals (Hazard Information and Packaging for Supply) Regulations. Obtain the relevant Material Safety Data Sheets and follow the advice given. These can be found at www.f-ball.co.uk alternatively these can be obtained from the point of purchase or from F. Ball and Co. Ltd. at the address below.

Site conditions vary, to ensure this product is suitable and confirm this data sheet is current please contact Technical Services Department.

For further information about F. Ball products or more detailed technical assistance, please contact:

F. Ball and Co. Ltd.
Churnetside Business Park
Station Road, Cheddleton, Leek
Staffordshire ST13 7RS
United Kingdom

Tel: +44 (0) 1538 361633
Fax: +44 (0) 1538 361622
Tech Services Fax: +44 (0) 1538 361567
Email: mail@f-ball.co.uk
www.f-ball.co.uk